

# 11.900N | Brushed Silver

## Total Wrap | Speciality

### Features

The 11.900N | Brushed Silver film is a 110 micron textured cast PVC film. This Total Wrap product has been developed specifically for the vehicle wrapping market. By utilising cutting edge technology to combine the special PVC compounds together with high quality pigments, we can offer a film with incredible dimensional stability & long-term durability. Typical applications include vehicle graphics & signage projects that require an exterior service life of 5 years. This films is suitable for both indoor & outdoor environments.

### Technical & Performance Information

|                                    |                                       |
|------------------------------------|---------------------------------------|
| Film Thickness                     | 110 micron                            |
| Adhesive Thickness                 | 20 micron                             |
| Total Thickness                    | 130 micron                            |
| Adhesive Type                      | Black permanent solvent based acrylic |
| Release Liner                      | 130 gsm PE coated kraft liner         |
| Artificial Weathering *            | ~5 years                              |
| Film Tensile Strength MD           | - N/mm <sup>2</sup>                   |
| Film Elongation MD                 | > 150 %                               |
| Adhesion to steel (20 mins / 180°) | 10 N/25mm                             |
| Adhesion to steel (24 hrs / 180°)  | 15 N/25mm                             |
| Dimensional Stability              | < 0.3 mm                              |
| Application Temperature            | +8 to +25°C                           |
| Service Temperature                | -45 to +110°C                         |
| Release Liner                      | Neutral                               |

\* equivalent to vertical exposure in Mid-European climate

### Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if not measured values are different

Groendreef 35  
 B-9880 Aalter | Belgium  
 T +32 9 216 6700  
 F +32 9 216 6709  
 W [www.isee2.eu](http://www.isee2.eu)