

## 73.900N | Chrome Silver Total Wrap | Speciality

### Features

73.900N | Chrome Silver is a highly reflective silver PVC laminated film construction. The product is coated with a permanent clear acrylic solvent-based pressure sensitive adhesive system. Applied with care, this product can be applied around complex curves and as such be used for short term vehicle applications e.g. wrapping wing mirrors, without significant matting. The film also offers good scratch resistance. In case our 73.900N is plotter cut and used for graphic lettering, please ensure proper sealing of the edges. As our 73.900N is a metalized film, it requires edge sealing to fall under our warantee. We recommend to use our 97.000 | iSee2 Sealitpen.

This film comes in 1370mm width .

### Technical & Performance Information

Film Thickness	100 micron
Adhesive Thickness	16 micron
Total Thickness	116 micron
Adhesive Type	Permanant clear solvent based acrylic
Release Liner	140 gsm PE coated kraft liner
Artificial Weathering *	> 3 years
Film Tensile Strength MD	> 30N/mm <sup>2</sup>
Film Elongation MD	> 50%
Adhesion to steel (20 mins / 180°)	15N/25mm
Adhesion to steel (24 hrs / 180°)	18N/25mm
Dimensional Stability	< 1%
Application Temperature	+10 to +25°C
Service Temperature	- 30 to +70°C
Release liner	Neutral
If plotter cut	Requires edge sealing with 97.000   iSee2 Sealitpen

\* equivalent to vertical exposure in Mid-European climate

### Warranty

iSee2 warrantees our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrantees our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if not measured values are different

Groendreef 35  
B-9880 Aalter | Belgium  
T +32 9 216 6700  
F +32 9 216 6709  
W [www.isee2.eu](http://www.isee2.eu)