

21.001N | SlipStop 120

Features

21.001N | SlipStop 120 is a clear matt textured polypropylene film suitable for indoor use. This product is developed as an anti-slippery overlamination for floor decals, roll-ups, table and counter top applications. Being a polypropylene, it is an economical and environmental friendly alternative to PVC films. The SlipStop 120 offers a permanent acrylic adhesive, formulated to give exceptional clarity and bond strength. The adhesive will perform impeccably on most common printing inks. In case of specific ink formulations however, we advise to test before use.

In order to achieve a perfect end result, we recommend to combine the SlipStop 120 lamination film with our 40.100N | StrongTack (permanent) or the 51.101N | StrongTouch (removable) print film.

21.001N | SlipStop 120 is available in 1370mm (width) x 50m (length) rolls.

Technical & Performance Information

Film Thickness	120 micron
Adhesive Thickness	25 micron
Total Thickness	145 micron
Adhesive type	High tack permanent clear waterbased acrylic
Release Liner	70 g/m ² liner
Artificial Weathering*	2 years
Adhesion to steel (24 hrs / 180°)**	18 N/25mm
Dimensional Stability	Excellent
Application Temperature	+10 to +25 °C
Service Temperature	-40 to +80 °C

* equivalent to vertical exposure in Mid-European climate

** tests are still ongoing

Certifications

Anti-Slip Rating	R9
------------------	----

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.