

51.104N | Total Eraze Matt White

Features

51.104N | Total Eraze Matt White is a matt white polymeric vinyl used for whiteboard applications. The PVC film is top coated with a low energy lacquer to ensure clean removal of the ink used in dry erase markers and carries a High Tack Permanent adhesive, which allows application on difficult substrates such as painted walls. This whiteboard film imparts a very high opacity level due to the grey tinted adhesive system and the thickness of the film. Thanks to its anti-glare properties, the preferred choice when used in combination with a beamer.

In order to achieve the best installation results, this film should be applied at room temperature and on smooth surfaces only. Please always check the suitability of the whiteboard marker ink prior to installation. We recommend using our 97.011 | Eraze Marker black or, when using different markers, to consult the 'Total Eraze marker compatibility list'.

51.104N | Total Eraze Matt White is available in 1350mm (width) x 50m (length) rolls.

Technical & Performance Information

Film Thickness	150 micron
Adhesive Thickness	20 micron
Total Thickness	170 micron
Adhesive type	Grey tinted high tack permanent acrylic
Release Liner	One sided silicone-coated kraft liner
Artificial Weathering*	3 years
Film Tensile Strength MD	>15 N/mm ²
Film Elongation MD	>80%
Opacity	>96%
Adhesion to steel (20 mins / 180°)	13 N/25mm
Adhesion to steel (24 hrs / 180°)	21 N/25mm
Application Temperature	+5 to +25°C
Service Temperature	-40 to +95°C

* equivalent to vertical exposure in Mid-European climate

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.