# i**5**2

## 51.125N | Crystal Etch

#### **Features**

**51.125N | Crystal Etch** is a high quality polymeric film with the appearance of a (crystal) etched glass effect. This PVC film is intended for use in all exterior marking, specially formulated for producing fine window decals. The polymeric film is printable with (eco)solvent, UV and latex inks and has excellent cutting and weeding properties.

51.125N | Crystal Etch is available in both 1220mm & 1520mm (width) x 50m (length) rolls.

#### **Technical & Performance Information**

Film Thickness	70 micron
Adhesive Thickness	25 micron
Total Thickness	95 micron
Adhesive type	Permanent pressure sensitive acrylic
Release Liner	140 gsm PE coated lay flat kraft liner
Artificial Weathering*	> 7 years
Film Tensile Strength MD	> 45 N/25mm
Film Elongation MD	> 180%
Adhesion to steel (20 mins / 180°)	15 N/25mm
Adhesion to steel (24 hrs / 180°)	20 N/25mm
Dimensional Stability	< 0,5mm
Application Temperature	+5 to +60 °C
Service Temperature	-30 to +110 °C
Opacity Level	Medium to high
Printability	(eco)solvent, UV & latex

\* equivalent to vertical exposure in Mid-European climate

### Certifications

Fire Rating

B-s2,d0 - Classification compliant with BS EN 13501-1:2007

#### Warranty

Groendreef 35 9880 Aalter, Belgium T +32 9 216 67 00 E info@iSee2.eu W www.iSee2.eu iSee2 warrantees our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrantees our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.